

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
24 April 2003 (24.04.2003)

PCT

(10) International Publication Number  
**WO 03/033138 A1**(51) International Patent Classification<sup>7</sup>: **B01J 23/68**,  
23/52, C07C 51/25, 51/215MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,  
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,  
VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/GB02/04018

(22) International Filing Date:  
4 September 2002 (04.09.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0124835.0 16 October 2001 (16.10.2001) GB  
0218870.4 13 August 2002 (13.08.2002) GB(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,  
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

## Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

## Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(71) Applicant (*for all designated States except US*): BP  
**CHEMICALS LIMITED** [GB/GB]; Britannic House, 1  
Finsbury Circus, London EC2M 7BA (GB).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): **ELLIS, Brian**  
[GB/GB]; 38 Hawkewood Road, Lower Sunbury, Middle-  
sex TW16 6HJ (GB).(74) Agent: **BROOKE, Caron**; BP International Limited,  
Patents & Agreements, Chertsey Road, Sunbury on  
Thames, Middlesex TW16 7LN (GB).(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,

(54) Title: ETHANE OXIDATION CATALYST AND PROCESS UTILISING THE CATALYST

(57) Abstract: A catalyst composition and its use for the selective oxidation of ethane to acetic acid and/or for the selective oxidation of ethylene to acetic acid which composition comprises in combination with oxygen the elements molybdenum, vanadium, niobium, gold in the absence of palladium according to the empirical formula:  $\text{Mo}_a\text{W}_b\text{Au}_c\text{V}_d\text{Nb}_e\text{Z}_f$  wherein Z is one or more elements selected from the group consisting of B, Al, Ga, In, Ge, Sn, Pb, Sb, Cu, Pt, Ag, Fe and Re; a, b, c, d, e and f represent the gram atom ratios of the elements such that:  $0 < a \leq 1$ ;  $0 \leq b < 1$  and  $a + b = 1$ ;  $10^{-5} \phi \leq 0.02$ ;  $0 < d \leq 2$ ;  $0 < e \leq 1$ ; and  $0.0001 \leq f \leq 0.05$ .

### ETHANE OXIDATION CATALYST AND PROCESS UTILISING THE CATALYST

The present invention relates to a catalyst for the selective oxidation of ethane to acetic acid and/or for the selective oxidation of ethylene to acetic acid, and to a process for the production of acetic acid utilising the aforesaid catalyst.

Catalysts comprising molybdenum, vanadium and niobium in combination with  
5 oxygen for use in processes for the production of acetic acid by the oxidation of ethane and ethylene are known in the art from, for example, US 4,250,346, EP-A-1043064, WO 99/20592 and DE 196 30 832.

US Patent No. 4,250,346 discloses the oxidative dehydrogenation of ethane to ethylene in a gas phase reaction at relatively high levels of conversion, selectivity and  
10 productivity to ethylene at a temperature of less than about 550°C using as a catalyst a composition comprising the elements molybdenum, X and Y in the ratio  $Mo_aX_bY_c$  wherein X is Cr, Mn, Nb, Ta, Ti, V and/or W, and preferably Mn, Nb, V and/or W; Y is Bi, Ce, Co, Cu, Fe, K, Mg, Ni, P, Pb, Sb, Si, Sn, Tl and/or U, and preferably Sb, Ce and/or U, a is 1, b is 0.05 to 1.0 and c is 0 to 2, and preferably 0.05 to 1.0, with the  
15 proviso that the total value of c for Co, Ni and/or Fe is less than 0.5.


WO 99/20592 relates to a method of selectively producing acetic acid from ethane, ethylene or mixtures thereof and oxygen at high temperature in the presence of a catalyst having the formula  $Mo_aPd_bX_cY_d$  wherein X represents one or several of Cr, Mn, Nb, Ta, Ti, V, Te and W; Y represents one or several of B, Al, Ga, In, Pt, Zn, Cd, Bi,  
20 Ce, Co, Rh, Ir, Cu, Ag, Au, Fe, Ru, Os, K, Rb, Cs, Mg, Ca, Sr, Ba, Nb, Zr, Hf, Ni, P, Pb, Sb, Si, Sn, Tl and U and  $a=1$ ,  $b=0.0001$  to  $0.01$ ,  $c=0.4$  to  $1$  and  $d=0.005$  to  $1$ .

German patent application DE 196 30 832 A1 relates to a similar catalyst

composition in which  $a=1$ ,  $b > 0$ ,  $c > 0$  and  $d = 0$  to  $2$ . Preferably,  $a = 1$ ,  $b = 0.0001$  to  $0.5$ ,  $c = 0.1$  to  $1.0$  and  $d = 0$  to  $1.0$ .

The catalysts of both WO 99/20592 and DE 19630832 require the presence of palladium.

5 EP-A-1043064 discloses a catalyst composition for the oxidation of ethane to ethylene and/or acetic acid and/or for the oxidation of ethylene to acetic acid which comprises in combination with oxygen the elements molybdenum, vanadium, niobium and gold in the absence of palladium according to the empirical formula :



10 wherein Y is one or more elements selected from the group consisting of : Cr, Mn, Ta, Ti, B, Al, Ga, In, Pt, Zn, Cd, Bi, Ce, Co, Rh, Ir, Cu, Ag, Fe, Ru, Os, K, Rb, Cs, Mg, Ca, Sr, Ba, Zr, Hf, Ni, P, Pb, Sb, Si, Sn, Tl, U, Re, Te, La and Pd;  $a$ ,  $b$ ,  $c$ ,  $d$ ,  $e$  and  $f$  represent the gram atom ratios of the elements such that :  $0 < a \leq 1$ ;  $0 \leq b < 1$  and  $a + b = 1$ ;  $10^{-5} < c \leq 0.02$ ;  $0 < d \leq 2$ ;  $0 < e \leq 1$ ; and  $0 \leq f \leq 2$ .

15 There remains a need to develop a catalyst for the oxidation of ethane and/or ethylene to acetic acid and a process for the production of acetic acid using said catalyst and wherein the catalyst enables a high selectivity to acetic acid to be achieved.

Surprisingly, it has now been found that it is possible by using a catalyst that contains, in combination with oxygen, the elements molybdenum, vanadium, niobium  
20 and gold and one or more elements selected from the group consisting of boron, aluminium, gallium, indium, germanium, tin, lead, antimony, copper, platinum, silver, iron and rhenium, in the absence of palladium, to oxidise ethane and/or ethylene to acetic acid with a high selectivity to acetic acid. Furthermore, it has been found possible  
25 using the catalysts of the present invention, to achieve a high selectivity to acetic acid with reduced, for example, little, if any, selectivity to ethylene.

Accordingly, the present invention provides a catalyst composition for the selective oxidation of ethane to acetic acid and/or for the selective oxidation of ethylene to acetic acid which composition comprises in combination with oxygen the elements molybdenum, vanadium, niobium, gold in the absence of palladium

30 according to the empirical formula :  $\text{Mo}_a\text{W}_b\text{Au}_c\text{V}_d\text{Nb}_e\text{Z}_f \quad (\text{I})$

wherein Z is one or more elements selected from the group consisting of B, Al, Ga, In, Ge, Sn, Pb, Sb, Cu, Pt, Ag, Fe and Re;

a, b, c, d, e and f represent the gram atom ratios of the elements such that :

$$0 < a \leq 1; 0 \leq b < 1 \text{ and } a + b = 1;$$



$$10^{-5} < c \leq 0.02;$$

$$0 < d \leq 2;$$

$$0 < e \leq 1; \text{ and}$$




$$0.0001 \leq f \leq 0.05$$

Catalysts embraced within the formula (I) include:-



10 Preferably, Z is Sn, Ag, Fe or Re, especially Sn.

Examples of suitable catalysts having the formula (I) include:-



15  $\text{Mo}_{1.00}\text{V}_{0.423}\text{Nb}_{0.115}\text{Au}_{0.0008}\text{Sn}_{0.0008}\text{O}_y$ , and

$\text{Mo}_{1.00}\text{V}_{0.423}\text{Nb}_{0.117}\text{Au}_{0.0008}\text{Sn}_{0.0156}\text{O}_y$ , wherein y is a number which satisfies the valencies of the elements in the composition for oxygen.

Preferably  $0.01 < a \leq 1$ . Preferably,  $0.1 < d \leq 2$ . Preferably,  $0.01 < e \leq 0.5$ , for example,  $0.05 \leq e \leq 0.15$ . Preferably,  $0.0005 \leq f \leq 0.02$ .

20 An advantage of the catalyst compositions of the present invention is that they are highly selective in converting ethane and/or ethylene to acetic acid. Typically, using the catalyst compositions of the present invention, a selectivity to acetic acid of at least 50mol%, preferably at least 60mol%, such as at least 70mol%, may be achieved.

25 In particular, using the catalyst compositions of the present invention, a high selectivity to acetic acid may be achieved in combination with a low, if any, selectivity to ethylene.

Typically, using the catalyst compositions of the present invention, the selectivity to ethylene is less than 25 mol%, preferably, less than 10 mol%, such as less than 5 mol%.

30 Preferably, using the catalyst compositions of the present invention, the selectivity to acetic acid is at least 60mol%, such as at least 70mol% and the selectivity to ethylene is less than 15mol%, such as less than 10 mol%.

As used herein, selectivity refers to a percentage that reflects the amount of desired acetic acid product produced as compared to the total carbon in the products formed :-

$$\% \text{ selectivity} = 100 * \text{Moles of acetic acid produced} / S$$

- 5 wherein S = the molar acid-equivalent sum (carbon basis) of all carbon-containing products, excluding the alkane in the effluent

The catalyst compositions may be prepared by any of the methods conventionally employed for the preparation of catalysts. Suitably the catalyst may be prepared from a solution of soluble compounds and/or complexes and/or compounds of  
10 each of the metals. The solution is preferably an aqueous system having a pH in the range from 1 to 12, preferably from 2 to 8, at a temperature of from 20° to 100°C.

Generally, a mixture of compounds containing the elements is prepared by dissolving sufficient quantities of soluble compounds and dispersing any insoluble compounds so as to provide a desired gram-atom ratio of the elements in the catalyst  
15 composition. The catalyst composition may then be prepared by removing the solvent from the mixture. The catalyst may be calcined by heating to a temperature of from 200 to 550°C, suitably in air or oxygen, for a period of from 1 minute to 24 hours. Preferably, the air or oxygen is slowly flowing.

The catalyst may be used unsupported or supported. Suitable supports include  
20 silica, alumina, zirconia, titania, silicon carbide and mixtures of two or more thereof.

Further details of a suitable method for preparing a catalyst composition may be found in, for example, EP-A-0166438.

The catalyst may be used in the form of a fixed or a fluidised bed.

In another embodiment the present invention provides a process for the selective  
25 production of acetic acid from a gaseous mixture comprising ethane and/or ethylene which process comprises contacting the gaseous mixture with a molecular oxygen-containing gas at elevated temperature in the presence of a catalyst composition as hereinbefore described.

Ethane is selectively oxidised to acetic acid and/or ethylene is selectively  
30 oxidised to acetic acid. Preferably, ethane and optionally ethylene is oxidised to a mixture comprising acetic acid which may be used with or without the addition or removal of acetic acid for the production of vinyl acetate by reaction with a molecular

oxygen-containing gas in an integrated process.

The feed gas comprises ethane and/or ethylene, preferably ethane.

5 Ethane and/or ethylene may be used in substantially pure form or admixed with one or more of nitrogen, methane, carbon dioxide and water in the form of steam, which may be present in major amounts, for example greater than 5 volume percent or one or more of hydrogen, carbon monoxide, C<sub>3</sub>/C<sub>4</sub> alkenes and alkenes, which may be present in minor amounts, for example less than 5 volume percent.

10 The molecular oxygen-containing gas may be air or a gas richer or poorer in molecular oxygen than air, for example oxygen. A suitable gas may be, for example, oxygen diluted with a suitable diluent, for example nitrogen.

It is preferred to feed, in addition to ethane and/or ethylene and the molecular oxygen-containing gas, water (steam) because this can improve the selectivity to acetic acid.

15 The elevated temperature may suitably be in the range from 200 to 500°C, preferably from 200 to 400°C.

The pressure may suitably be atmospheric or superatmospheric, for example in the range from 1 to 50 bar, preferably from 1 to 30 bar.

20 The catalyst composition is preferably calcined before use in the process of the invention. Calcination may suitably be achieved by heating at a temperature suitably in the range from 250 to 500°C in the presence of an oxygen-containing gas, for example air.

Operating conditions and other information applicable to the performance of the invention may be found in the aforesaid prior art, for example US Patent No. 4,250,346.


25 The process of the invention will now be further illustrated by reference to the following Examples.

### **CATALYST PREPARATION**

#### **Preparation of Catalyst A (Comparative)**

30 A solution 'A' was prepared by dissolving 22.935 g of ammonium molybdate and 0.0357 g of ammonium gold chloride in 100 ml of distilled water at 70°C with stirring. A solution 'B' was prepared by dissolving 6.434 g of ammonium vanadate in 150 ml of distilled water at 70°C with stirring. A solution 'C' was prepared by dissolving 7.785 g of ammonium niobium oxalate in 100 ml of distilled water at 70°C


with stirring. Each of the solutions A, B and C was left for 15 minutes to allow maximum solubilisation of the components. Solution C was then added to solution B rapidly with stirring at 70°C. The mixed solution B/C was stirred for 15 minutes at 70°C then added rapidly to solution A. The final mixed solution A/B/C was left to stir at 70°C for a further 15 minutes, after which the solution was heated to boiling to facilitate evaporation of the water. Full evaporation of the reactant mixture was achieved in 1.5 hours, resulting in a dry paste. The beaker with the dried paste was then transferred to an oven for further drying at 120°C for 2 hours. After drying, the catalyst precursor was ground to a fine powder and then sieved through a 0.2 mm mesh sieve. The resulting powdered catalyst cake was then calcined in static air in an oven at 400°C for 4 hours. The nominal formula of the oxide catalyst obtained was :



This catalyst is not a catalyst according to the invention because it contains no element from the group consisting of B, Al, Ga, In, Ge, Sn, Pb, Sb, Cu, Pt, Ag, Fe and Re.


#### **Preparation of Catalyst B**

A catalyst B was prepared as for catalyst A except that 0.0190 g of tin (II) chloride was additionally added to solution A. The nominal formula of the oxide catalyst obtained was :




#### **Preparation of Catalyst C**

A catalyst C was prepared as for catalyst A except that 0.3792 g of tin (II) chloride was added to solution A. The nominal formula of the oxide catalyst obtained was :




#### **Preparation of catalyst D**

A catalyst D was prepared as for catalyst A but with addition of 0.0299 g of antimony (III) acetate (FW 298.88) to solution A. The nominal formula of the oxide catalyst was thus :




#### **Preparation of catalyst E**

A catalyst E was prepared as for catalyst A but with addition of 0.0200 g of copper (II) acetate (FW 199.65) to solution A. The nominal formula of the oxide catalyst was thus :




#### 5 Preparation of catalyst F

A catalyst F was prepared as for catalyst A but with addition of 0.0027 g of platinum acetate (FW 352.66) to solution A. The nominal formula of the oxide catalyst was thus :




#### 10 Preparation of catalyst G

A catalyst G was prepared as for catalyst A but with addition of 0.0174 g of silver (I) acetate (FW 166.92) to solution A. The nominal formula of the oxide catalyst was thus :




#### 15 Preparation of catalyst H

A catalyst H was prepared as for catalyst A but with addition of 0.8080 g of ferric (III) nitrate (FW 404.00) to solution A. The nominal formula of the oxide catalyst was thus :




#### 20 Preparation of catalyst I

A catalyst I was prepared as for catalyst A but with addition of 0.0268 g of ammonium rhenate (FW 268.24) to solution A. The nominal formula of the oxide catalyst was thus :



#### 25 Preparation of catalyst J

A catalyst J was prepared as for catalyst A but with addition of 0.0256 g of gallium nitrate (FW 255.74) to solution A. The nominal formula of the oxide catalyst was thus :



#### 30 General Ethane Oxidation Reaction Method

Typically 5 ml of a powdered catalyst A to J was mixed with 15 ml of glass beads of diameter 0.4 mm to form a diluted catalyst bed of 20 ml in volume. The diluted



catalyst was then loaded into a fixed bed reactor made of Hastelloy of dimensions 12 mm internal diameter and length 40 cm. The catalyst was maintained in position in the centre of the reactor using quartz wall plugs with inert packing material above and below the catalyst bed. The apparatus was then pressure-tested at 20 bar with helium to check for leaks. The catalyst was then activated by heating to 220°C at 5°C/min in helium at 16 bar for 1 hour, to ensure full decomposition of catalyst precursors.

The required flows of ethane, ethylene, 20 % oxygen in helium and water were then introduced to the reactor, to ensure the required inlet composition. This composition was 52 % v/v ethane, 6.7 % v/v oxygen, 10 % v/v ethylene, 5 % v/v water and balance helium. The total feed flow rate was maintained at a level to ensure a feed GHSV of 2000-9000/h. After equilibrating for 60 minutes, gas samples were taken from the outlet stream to a GC system (model Unicam 4400) to quantify ethane, ethylene, oxygen and helium.

The setpoint temperature of the reactor was increased to 293°C, to achieve a similar reactor temperature of 299-301°C for each of catalysts A-J, in order to facilitate direct comparison. Following a further equilibration period of 60 minutes, liquid product collection was commenced and continued for a period of typically 18 hours. During the run period, the effluent gas composition was measured using GC analysis (ProGC, Unicam). Exit gas volume was measured over the run period by a water-gas meter. The liquid products were collected and weighed after the run period. Composition of the liquid products was measured using gas chromatography analysis (Unicam 4400 and 4200 fitted with TCD and FID detectors respectively).

From analysis of the feed and product flow rates and compositions the following parameters were calculated :

#### 25 Conversions:

of ethane = (inlet mol ethane - outlet mol ethane) / inlet mol ethane \* 100

of oxygen = (inlet mol oxygen - outlet mol oxygen) / inlet mol oxygen \* 100

#### Selectivities :

to acetic acid (C-mol %) = (outlet mol acetic acid \* 2) / ((outlet mol ethylene \* 2 - inlet mol ethylene \* 2) + outlet mol CO + outlet mol CO<sub>2</sub> + outlet mol acetic acid \* 2) \* 100

to ethylene (C-mol %) = (outlet mol ethylene \* 2) / ((outlet mol ethylene \* 2 - inlet mol

ethylene \* 2) + outlet mol CO + outlet mol CO<sub>2</sub> + outlet mol acetic acid \* 2) \* 100  
 to CO (C-mol %) = (outlet mol CO) / ((outlet mol ethylene \* 2 – inlet mol ethylene \*  
 2) + outlet mol CO + outlet mol CO<sub>2</sub> + outlet mol acetic acid \* 2) \* 100  
 to CO<sub>2</sub> (C-mol %) = (outlet mol CO<sub>2</sub>) / ((outlet mol ethylene \* 2 – inlet mol ethylene \*  
 2) + outlet mol CO + outlet mol CO<sub>2</sub> + outlet mol acetic acid \* 2) \* 100  
 to CO<sub>x</sub> = selectivity to CO (C-mol %) + selectivity to CO<sub>2</sub> (C-mol %)  
 STY (space time yield)% = (g acetic acid)/kg catalyst bed /hour

Typically, mass balance and carbon balance for a reaction was found to be 100 .  
 +/- 5 %.

#### 10 **Experiment A and Examples 1 to 9**

Each catalyst A to J was employed in the general reaction method described above. The results are given in Tables 1. Each catalyst was evaluated under standard conditions indicated in Table 1.

**Table 1**

Experiment	Catalyst	Ethane Convn % C-mol	Sel. Acetic acid % C-mol	Sel. C <sub>2</sub> H <sub>4</sub> % C-mol	Sel CO <sub>x</sub> % C-mol	STY AcOH g/kg-cat/h
A	A	7.8	47.0	34.4	18.5	163
Example 1	B	4.2	71.3	0.0	28.7	118
Example 2	C	3.8	70.8	0.0	29.2	105
Example 3	D	6.3	56.9	24.7	18.5	133.6
Example 4	E	4.1	58.4	12.9	28.7	85.9
Example 5	F	5.1	59.9	12.6	27.4	112.7
Example 6	G	3.1	63.4	1.7	34.9	99.8
Example 7	H	4.7	68.1	5.6	26.4	119.3
Example 8	I	5.0	70.1	5.7	24.2	131.1
Example 9	J	5.8	53.9	27.5	18.7	115.8


15 Conditions:

52 % v/v ethane, 6.7% v/v oxygen, 10% v/v ethylene, 5 % v/v water , balance helium.  
 GHSV = 3200 h<sup>-1</sup>; 16 bar

The results in Table 1 clearly demonstrate that compared to the comparison catalyst, catalyst A, the catalysts of the present invention achieve higher selectivities to  
 20 acetic acid. Furthermore, a high selectivity to acetic acid is achieved in combination with reduced selectivity to ethylene.

## Claims:

1. A catalyst composition for the selective oxidation of ethane to acetic acid and/or for the selective oxidation of ethylene to acetic acid which composition comprises in combination with oxygen the elements molybdenum, vanadium, niobium, gold in the absence of palladium according to the empirical formula :



wherein Z is one or more elements selected from the group consisting of B, Al, Ga, In, Ge, Sn, Pb, Sb, Cu, Pt, Ag, Fe and Re;

a, b, c, d, e and f represent the gram atom ratios of the elements such that :

10 
$$\begin{aligned} 0 < a \leq 1; & 0 \leq b < 1 \text{ and } a + b = 1; \\ 10^{-5} < c & \leq 0.02; \\ 0 < d & \leq 2; \\ 0 < e & \leq 1; \text{ and} \\ 0.0001 & \leq f \leq 0.05 \end{aligned}$$

2. A catalyst composition as claimed in claim 1 wherein  $0.01 < a \leq 1$ ,  $0.1 < d \leq 2$ ,  
15  $0.01 < e \leq 0.5$  and  $0.0005 \leq f \leq 0.02$ .

3. A catalyst composition as claimed in any preceding claim wherein Z is Sn, Ag, Fe or Re.

4. A catalyst composition as claimed in claim 3 wherein Z is Sn.

5. A catalyst composition as claimed claim 4 wherein formula I is selected from the  
20 group consisting of  $\text{Mo}_a\text{W}_b\text{Au}_c\text{V}_d\text{Nb}_e\text{Sn}_f$  and  $\text{Mo}_a\text{Au}_c\text{V}_d\text{Nb}_e\text{Sn}_f$ .

6. A catalyst composition as claimed in claim 1 having the formula selected from the group consisting of  $\text{Mo}_{1.000}\text{V}_{0.423}\text{Nb}_{0.115}\text{Au}_{0.008}\text{Ag}_{0.008}\text{O}_y$ ,  $\text{Mo}_{1.000}\text{V}_{0.423}\text{Nb}_{0.115}$

$\text{Au}_{0.008} \text{Fe}_{0.0156} \text{O}_y, \text{Mo}_{1.000} \text{V}_{0.423} \text{Nb}_{0.115} \text{Au}_{0.008} \text{Re}_{0.008} \text{O}_y, \text{Mo}_{1.00} \text{V}_{0.423} \text{Nb}_{0.115} \text{Au}_{0.0008} \text{Sn}_{0.0008} \text{O}_y$ , and  $\text{Mo}_{1.00} \text{V}_{0.423} \text{Nb}_{0.117} \text{Au}_{0.0008} \text{Sn}_{0.0156} \text{O}_y$ , wherein  $y$  is a number which satisfies the valencies of the elements in the composition for oxygen.

7. A process for the production of acetic acid from a gaseous mixture comprising ethane and/or ethylene which process comprises contacting the gaseous mixture with a molecular oxygen-containing gas at elevated temperature in the presence of a catalyst composition as claimed in any one of the preceding claims.

8. A process as claimed in claim 7 in which ethane and optionally ethylene is oxidised to a mixture comprising acetic acid.

9. A process as claimed in claim 7 or claim 8 in which the elevated temperature is in the range from 200 to 500°C.

10. A process as claimed in any one of claims 7 to 9 in which the pressure is the range from 1 to 50 bar.

11. A process as claimed in any one of claims 7 to 10 in which the selectivity of the oxidation reaction of ethane and/or ethylene to acetic acid is at least 50mol%.

12. A process as claimed in claim 11 in which the selectivity of the oxidation reaction of ethane and/or ethylene to acetic acid is at least 60mol%.

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J23/68 B01J23/52 C07C51/25 C07C51/215

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, INSPEC, COMPENDEX

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 043 064 A (BP CHEM INT LTD) 11 October 2000 (2000-10-11) cited in the application paragraphs '0011!', '0022!', '0028!', '0029! example 1 -----	1-12
X	WO 99 51339 A (JONES MICHAEL DAVID ;KITCHEN SIMON JAMES (GB); COOK JOHN (GB); ELL) 14 October 1999 (1999-10-14) page 4, line 13 -page 5, line 13 page 6, line 11 - line 31 -----	1, 3, 7-12
E	EP 1 192 987 A (ROHM & HAAS) 3 April 2002 (2002-04-03) paragraph '0024!; examples 12-14 ----- -/--	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents:

- 'A' document defining the general state of the art which is not considered to be of particular relevance
- 'E' earlier document but published on or after the international filing date
- 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- 'O' document referring to an oral disclosure, use, exhibition or other means
- 'P' document published prior to the international filing date but later than the priority date claimed

- 'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- 'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- 'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- 'Z' document member of the same patent family

Date of the actual completion of the international search

28 November 2002

Date of mailing of the international search report

05/12/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Besselmann, S

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 274 765 B1 (ROESKY RANIER ET AL) 14 August 2001 (2001-08-14) the whole document	

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1043064	A	11-10-2000	BR 0001460 A	16-01-2001
			CN 1269259 A	11-10-2000
			EP 1043064 A2	11-10-2000
			JP 2000312826 A	14-11-2000
			NO 20001678 A	02-10-2000
			SG 84569 A1	20-11-2001
			TR 200000876 A2	21-11-2000
			TW 476666 B	21-02-2002
			US 6333444 B1	25-12-2001
WO 9951339	A	14-10-1999	AU 3160899 A	25-10-1999
			BR 9909164 A	16-10-2001
			CN 1303320 T	11-07-2001
			EP 1069945 A1	24-01-2001
			WO 9951339 A1	14-10-1999
			JP 2002510543 T	09-04-2002
			NO 20004909 A	17-11-2000
			TR 200002817 T2	21-12-2000
			US 6350716 B1	26-02-2002
EP 1192987	A	03-04-2002	US 2002065431 A1	30-05-2002
			CN 1347756 A	08-05-2002
			EP 1192987 A1	03-04-2002
			JP 2002177784 A	25-06-2002
			BR 0104285 A	07-05-2002
US 6274765	B1	14-08-2001	DE 19717076 A1	29-10-1998
			CN 1090605 B	11-09-2002
			DE 59803069 D1	21-03-2002
			WO 9847850 A1	29-10-1998
			EP 0979222 A1	16-02-2000
			ES 2172145 T3	16-09-2002
			JP 2001524089 T	27-11-2001
			NO 995085 A	18-10-1999